Ravathane R210A90UV

Thermoplastic Polyurethane Elastomer (Polyether)

RAVAGO Kimya Plastik Sanayi ve Ticaret A.S.

Message:

Description: Product is based on standard grade polyether and has strong resilience and tear resistance, excellent abrasion resistance, excellent resistance to hydrolysis failure and microbial attack, good stability towards solvents and light. Application: Injection molding and extrusion

General Information				
Features	Antimicrobial			
	Good tear strength			
	Good wear resistance			
	Hydrolysis resistance			
	Elastic			
Forms	Particle			
Processing Method	Extrusion			
	Injection molding			
Physical	Nominal Value	Unit	Test Method	
Density	1.12	g/cm³	ISO 1183/A	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	91		ISO 868	
Mechanical	Nominal Value	Unit	Test Method	
Abrasion Resistance	35.0	mm³	ISO 4649	
Extruder Screw L/D Ratio	25:1			
Screw cooling	Air			
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress			ISO 37	
100% strain	8.00	MPa	ISO 37	
300% strain	18.0	MPa	ISO 37	
Tensile Stress (Yield)	42.0	MPa	ISO 37	
Tensile Elongation (Break)	550	%	ISO 37	
Tear Strength ¹	120	kN/m	ISO 34-1	
Injection	Nominal Value	Unit		
Drying Temperature	100 - 110	°C		
Rear Temperature	195	°C		
Middle Temperature	205	°C		
Front Temperature	210	°C		
Nozzle Temperature	205	°C		
Injection Pressure	70.0	MPa		

Extrusion	Nominal Value	Unit		
Cylinder Zone 1 Temp.	200 - 210	°C		
Cylinder Zone 2 Temp.	215 - 225	°C		
Cylinder Zone 3 Temp.	230 - 240	°C		
Cylinder Zone 4 Temp.	200 - 210	°C		
Die Temperature	200 - 210	°C		
Extrusion instructions				
Type: 30/25d, Screw: 3:1, Speed: 3:1, Speed: 50 rpm, Thickness Die: 0.2mm, Pre-heating: 1h@105°C				
NOTE				
1.	Method B, right-angle spo (cut)	ecimen		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

