

NEXUS PC PCFG30

Polycarbonate
Nexus Resin Group, LLC.

Message:
Molding Grade PC With 30% Glass

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.10 to 0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6210	MPa	ASTM D638
Tensile Strength (Yield)	117	MPa	ASTM D638
Flexural Modulus	6380	MPa	ASTM D790
Flexural Strength (Yield)	148	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	143	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	288 to 316	°C	
Middle Temperature	302 to 329	°C	
Front Temperature	316 to 343	°C	
Nozzle Temperature	316 to 343	°C	
Processing (Melt) Temp	316 to 343	°C	
Mold Temperature	79.4 to 107	°C	
Back Pressure	0.345 to 1.38	MPa	
Screw Speed	40 to 100	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

