

KOCETAL® K200

Acetal (POM) Copolymer

Kolon Plastics, Inc.

Message:

Kocetal K200 is suitable for both of injection molding and extrusion.

General Information			
Uses	Rods		
	Sheet		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	2.0	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60%RH)	0.22	%	ASTM D570

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ASTM D785

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	60.0	MPa	ASTM D638
Tensile Elongation (Yield, 23°C)	75	%	ASTM D638
Flexural Modulus (23°C)	2350	MPa	ASTM D790
Flexural Strength (23°C)	90.0	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	76	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	158	°C	
1.8 MPa, Unannealed	110	°C	
Vicat Softening Temperature	162	°C	ASTM D1525
Melting Temperature	166	°C	
CLTE - Flow	1.3E-4	cm/cm/°C	ASTM D696

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257

Dielectric Strength	19	kV/mm	ASTM D149
Dielectric Constant	3.70		ASTM D150
Dissipation Factor (1 MHz)	6.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Suggested Max Regrind	30	%	
Rear Temperature	160 to 180	°C	
Middle Temperature	180 to 190	°C	
Front Temperature	190 to 200	°C	
Nozzle Temperature	190 to 200	°C	
Processing (Melt) Temp	< 230	°C	
Mold Temperature	60.0 to 80.0	°C	
Injection Pressure	49.0 to 78.5	MPa	
Holding Pressure	29.4 to 49.0	MPa	
Back Pressure	0.981 to 2.94	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

