

CERTENE™ LLHF-122XH

Linear Low Density Polyethylene
Muehlstein

Message:

LLHF-122XH is a certified prime grade Ethylene-Hexene Copolymer specially developed for extrusion of SUPER STRENGTH Blown films of outstanding Impact and Toughness. LLHF-122XH features good processability and films exhibit exceptional Elmendorf Tear strength and Puncture resistance. LLHF-122XH major applications include super strong liners, lamination films, stretch wrapping films, and super strong carry-on-bags. Maximum recommended film drawdown is 0.3 mil. LLHF-122XH contains high slip and extra high antiblock. LLHF-122XH complies with FDA regulation 21CFR 177.1520 (c) 3.2(a) and most international regulations concerning the use of Polyethylene in contact with food articles.

General Information			
Additive	High smoothness		
	High caking resistance		
Features	Ultra-high impact resistance		
	Ultra high toughness		
	High smoothness		
	High caking resistance		
	High strength		
	Copolymer		
	hexene comonomer		
	Perforation resistance		
	Workability, good		
	Good tear strength		
	Compliance of Food Exposure		
Uses	Films		
	Lining		
	Heavy packing bag		
Agency Ratings	FDA 21 CFR 177.1520(c) 3.2a		
Forms	Particle		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	
secant modulus			ASTM D882
1% secant, MD	193	MPa	ASTM D882
1% secant, TD	207	MPa	ASTM D882

Tensile Strength			ASTM D882
MD: Yield, 25 µm	11.0	MPa	ASTM D882
TD: Yield, 25 µm	11.7	MPa	ASTM D882
MD: Break, 25 µm	55.2	MPa	ASTM D882
TD: Break, 25 µm	40.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Break, 25 µm	650	%	ASTM D882
TD: Break, 25 µm	780	%	ASTM D882
Dart Drop Impact ¹ (25 µm)	480	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD : 25 µm	430	g	ASTM D1922
TD : 25 µm	750	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.4 µm, Blown Film)	55		ASTM D2457
Haze (25.4 µm, Blown Film)	12	%	ASTM D1003
Additional Information			
Film Specimen: 1.0 mil (25 micron) film, melt temperature 420-450°F (215-230°C), blow-up-ratio 2.5 :1.			
NOTE			
1.	F50		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

