

PRL PPX-SF2

Polyphenylene Ether + PS

Polymer Resources Ltd.

Message:

PRL PPX-SF2 is a Polyphenylene Ether + PS (PPE+PS) product. It can be processed by structural foam molding and is available in North America. Typical application: Foam.

Characteristics include:

- Flame Rated
- RoHS Compliant
- Flame Retardant
- Halogen Free
- Heat Resistant

General Information			
UL YellowCard	E113219-100484392	E113219-101877587	
Additive	Flame Retardant		
Features	Bromine Free		
	Chlorine Free		
	Flame Retardant		
	Foamable		
	Medium Heat Resistance		
	Self Extinguishing		
Uses	Structural Foam		
RoHS Compliance	RoHS Compliant		
UL File Number	E113219		
Forms	Pellets		
Processing Method	Structural Foam Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.09	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/11.6 kg)	25 to 45	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.60 to 0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.18 mm	52.4	MPa	
Break, 3.18 mm	51.7	MPa	
Flexural Modulus (3.18 mm)	2410	MPa	ASTM D790
Flexural Strength (Break, 3.18 mm)	82.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	160	J/m	ASTM D256
Gardner Impact (3.18 mm)	16.9	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	104	°C	
1.8 MPa, Unannealed, 3.18 mm	98.9	°C	
RTI Elec			UL 746
3.00 mm	65.0	°C	
5.99 mm	65.0	°C	
RTI Imp			UL 746
3.00 mm	65.0	°C	
5.99 mm	65.0	°C	
RTI Str			UL 746
3.00 mm	65.0	°C	
5.99 mm	65.0	°C	
Flammability	Nominal Value	Test Method	
Flame Rating			UL 94
3.00 mm	V-0		
6.00 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 82.2	°C	
Drying Time	3.0 to 4.0	hr	
Drying Time, Maximum	8.0	hr	
Rear Temperature	232 to 260	°C	
Middle Temperature	271 to 304	°C	
Front Temperature	271 to 304	°C	
Processing (Melt) Temp	271 to 304	°C	
Mold Temperature	65.6 to 82.2	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

