

# Rotuba CAP CP801 (17% Plasticizer)

Cellulose Acetate Propionate

Rotuba Extruders, Inc.

## Message:

Rotuba CAP CP801 (17% Plasticizer) is a cellulose acetate propionate (CAP) product. It can be processed by injection molding and is available in North America. Rotuba CAP CP801 (17% Plasticizer) has applications including optics/lenses, containers and handles.

Features include:

environmental protection/green

Good dimensional stability

Good stiffness

good weather resistance

General Information			
Features	Good dimensional stability		
	Rigid, good		
	Updatable resources		
	Good strength		
	Good weather resistance		
Uses	Handle		
	Optical applications		
	Container		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.20 - 0.60	%	ASTM D955
Water Absorption (24 hr)	1.4	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	23.4	MPa	ASTM D638
Fracture	29.0	MPa	ASTM D638
Tensile Elongation (Break)	30	%	ASTM D638
Flexural Strength	33.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	450	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	71.7	°C	ASTM D648
Vicat Softening Temperature	91.1	°C	ASTM D1525
Injection	Nominal Value	Unit	

Processing (Melt) Temp	207	°C
Mold Temperature	43	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

