

YUNGSOX® PP 3015

Polypropylene Impact Copolymer

Formosa Polypropylene

Message:

YUNGSOX® PP 3015 is a Polypropylene Impact Copolymer (PP Impact Copolymer) material. It is available in Asia Pacific.

Important attributes of YUNGSOX® PP 3015 are:

Flame Rated

Impact Resistant

Copolymer

Good Stiffness

Typical applications include:

Containers

Consumer Goods

Food Contact Applications

Sporting Goods

General Information			
UL YellowCard	E216959-229353		
Features	Good Stiffness		
	High Impact Resistance		
	Impact Copolymer		
	Low Temperature Impact Resistance		
Uses	Industrial Containers		
	Luggage		
	Pails		
	Sporting Goods		
Agency Ratings	FDA 21 CFR 177.1520		
UL File Number	E216959		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.0	g/10 min	ISO 1133
Molding Shrinkage	1.3 to 1.7	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	95		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	27.5	MPa	ISO 527-2
Tensile Strain (Break)	450	%	ISO 527-2
Flexural Modulus	1100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180

-20°C	130	J/m	
23°C	490	J/m	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	110	°C	ISO 75-2/A
Vicat Softening Temperature	145	°C	ISO 306
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT