MAZMID B 153 SP20

Polyamide 6

Mazzaferro Indústria e Comércio de Polímeros e Fibras Ltda.

Message:

MAZMID B 153 SP20 is a Polyamide 6 (Nylon 6) product filled with 20% mineral. It can be processed by injection molding and is available in Latin America. Typical application: Automotive.

Characteristics include:

Flame Rated Good Aesthetics

Heat Stabilizer

General Information						
Filler / Reinforcement		Mineral,20% Filler by Weight				
Additive		Heat Stabilizer				
Features		Good Surface Finish				
		Heat Stabilized				
		Paintable				
Uses		Automotive Applications				
Appearance		Black				
		Colors Available				
		Grey				
		Natural Color				
Processing Method		Injection Molding				
Physical	Dry	Conditioned	Unit	Test Method		
Specific Gravity	1.32		g/cm³	ASTM D792		
Molding Shrinkage - Flow	1.0 to 1.3		%	ASTM D955		
Water Absorption (23°C, 24						
hr)	1.0 to 1.2		<u>%</u>	ASTM D570		
Hardness	Dry	Conditioned	Unit	Test Method		
Rockwell Hardness (R-Scale)	100	90		ASTM D785		
Mechanical	Dry	Conditioned	Unit	Test Method		
Tensile Modulus	4600	2200	MPa	ASTM D638		
Tensile Strength	60.0	50.0	MPa	ASTM D638		
Tensile Elongation (Break)	7.0	30	%	ASTM D638		
Flexural Modulus	3000	1600	MPa	ASTM D790		
Flexural Strength	100	55.0	MPa	ASTM D790		
Impact	Dry	Conditioned	Unit	Test Method		
Notched Izod Impact	60	110	J/m	ASTM D256		
Thermal	Dry	Conditioned	Unit	Test Method		
	,					

Deflection Temperature Under Load				ASTM D648
0.45 MPa, Unannealed	155		°C	7.51111.5010
1.8 MPa, Unannealed	110		°C	
Continuous Use Temperature	90.0 to 100		°C	
Melting Temperature	212 to 214		°C	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+12		ohms·cm	ASTM D257
Dielectric Strength	15		kV/mm	ASTM D149
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	V-2			UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

