

# Shin-Etsu Elastomer FE-281U

Fluorosilicone

Shin-Etsu Silicones of America

Message:

Catalyzed with 2,5-dimethyl-2,5-di(t-Butyl Peroxy) hexane 100% active at 0.65 parts per 100 base.  
Press cured 10 min. @ 170 °C.

General Information		
Physical	Nominal Value	Unit
Specific Gravity	1.70	g/cm <sup>3</sup>
Hardness	Nominal Value	Unit
Durometer Hardness	80	
Elastomers	Nominal Value	Unit
Tensile Strength	6.86	MPa
Additional Information		Nominal Value
Cure Agent	DBPH	

Press Cure / Post Cure: Post

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

