

VALOX™ VC130 resin

Polybutylene Terephthalate
SABIC Innovative Plastics Asia Pacific

Message:

VALOX™ VC130 resin is a Polybutylene Terephthalate (PBT) material. It is available in Asia Pacific. Primary attribute of VALOX™ VC130 resin: Flame Rated.

General Information			
UL YellowCard	E45587-236843		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.50	g/cm³	ASTM D792
Molding Shrinkage - Flow			Internal Method
3.20 mm	0.10 to 0.20	%	
6.40 mm	0.60 to 0.70	%	
Water Absorption (24 hr)	0.070	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	167	MPa	Internal Method
Tensile Elongation (Break)	3.0	%	Internal Method
Flexural Modulus	17500	MPa	ASTM D790
Flexural Strength	239	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	76	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.20 mm)	205	°C	ASTM D648
CLTE - Flow (-30 to 30°C)	5.0E-5	cm/cm/°C	ASTM E831
Flammability	Nominal Value		Test Method
Flame Rating (1.55 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT