

Generic Epoxy - Ceramic Bead

Epoxy; Epoxide

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic Epoxy - Ceramic Bead
This information is provided for comparative purposes only.

General Information			
Filler / Reinforcement	Ceramic Bead		
Hardness	Nominal Value	Test Method	
Durometer Hardness (23°C)	87 to 90	ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method
Compressive Strength (23°C)	75.8 to 108	MPa	ASTM D695
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	118 to 232	°C	ASTM D794
Thermoset	Nominal Value	Unit	
Pot Life (23°C)	28 to 46	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT