

Multilon® R-2010

Polycarbonate + ABS

TEIJIN LIMITED

Message:

Glass fiber reinforced PC/ABS polymer alloy, Automotive series

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Features	Rigidity, high		
	Heat resistance, high		
Uses	Application in Automobile Field		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/5.0 kg)	9.00	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal method
Transverse flow: 4.00mm	0.40 - 0.60	%	Internal method
Flow: 4.00mm	0.30 - 0.50	%	Internal method
Water Absorption (23°C, 24 hr)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3950	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	80.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	%	ISO 527-2/5
Flexural Modulus ¹ (23°C)	3800	MPa	ISO 178
Flexural Stress ² (23°C)	120	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	10	kJ/m ²	ISO 179
23°C	12	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	35	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	137	°C	ISO 75-2/B
1.8 MPa, not annealed	124	°C	ISO 75-2/A
Vicat Softening Temperature	130	°C	ISO 306/B50
Linear thermal expansion coefficient			ISO 11359-2
Flow	5.0E-5	cm/cm/°C	ISO 11359-2

Lateral	7.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT