

LNP™ THERMOCOMP™ WC006 compound

Polybutylene Terephthalate

SABIC Innovative Plastics

Message:

LNP THERMOCOMP WC006 is a compound based on PBT resin containing 30% Carbon Fiber. Added feature of this grade is: Electrically Conductive.

Also known as: LNP* THERMOCOMP* Compound WC-1006

Product reorder name: WC006

General Information			
Filler / Reinforcement	Carbon Fiber,30% Filler by Weight		
Features	Electrically Conductive		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.10 to 0.30	%	ASTM D955
Across Flow : 24 hr	1.0 to 2.0	%	ASTM D955
Across Flow : 24 hr	1.2	%	ISO 294-4
Flow : 24 hr	0.23	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	20000	MPa	ASTM D638
--	20700	MPa	ISO 527-2/1
Tensile Strength			
Yield	159	MPa	ASTM D638
Yield	158	MPa	ISO 527-2
Break	159	MPa	ASTM D638
Break	158	MPa	ISO 527-2
Tensile Elongation			
Yield	1.2	%	ASTM D638
Yield	1.3	%	ISO 527-2
Break	1.2	%	ASTM D638, ISO 527-2
Flexural Modulus			
--	15200	MPa	ASTM D790
--	17000	MPa	ISO 178
Flexural Strength			
--	207	MPa	ASTM D790
--	219	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	43	J/m	ASTM D256

23°C ²	4.6	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	460	J/m	ASTM D4812
23°C ³	29	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	8.40	J	ASTM D3763
--	2.40	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	223	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	223	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	211	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	209	°C	ISO 75-2/af
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	1.2E-5	cm/cm/°C	
Transverse : -40 to 40°C	6.8E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	221 to 232	°C	
Middle Temperature	243 to 254	°C	
Front Temperature	260 to 271	°C	
Processing (Melt) Temp	238 to 266	°C	
Mold Temperature	82.2 to 98.9	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

