

KOPLA PA66 KDT1020

Polyamide 66

KOPLA Co., Ltd.

Message:

KOPLA PA66 KDT1020 is a Polyamide 66 (Nylon 66) material filled with mineral. It is available in Asia Pacific.

Important attributes of KOPLA PA66 KDT1020 are:

Flame Rated

Good Dimensional Stability

Typical applications include:

Engineering/Industrial Parts

Housings

General Information			
Filler / Reinforcement	Mineral		
Features	Good Dimensional Stability		
Uses	Bushings		
	Housings		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Water Absorption (23°C, 24 hr)	0.50	%	ASTM D570

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	73.5	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	5.0	%	ASTM D638
Flexural Modulus (23°C)	4120	MPa	ASTM D790
Flexural Strength (23°C)	118	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	49	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	240	°C	
1.8 MPa, Unannealed	225	°C	
Melting Temperature	260	°C	
CLTE - Flow	6.5E-5	cm/cm/°C	ASTM D696

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	20	kV/mm	ASTM D149

Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

