

MAJORIS FT365 - 8479

Polypropylene

AD majoris

Message:

FT365 - 8479 is a 30% mineral filled polypropylene compound intended for injection moulding.

The product is available in natural FT365 but other colours can be provided on request.

FT365 - 8479 has been developed especially for automotive interior parts that requiring excellent scratch resistance, good balance between the impact strength and stiffness and very good surface quality. In addition it has a good UV stability and antistatic.

APPLICATIONSS

Consoles

Cowl vent grilles

Door panels and pockets

Handles

General Information			
Filler / Reinforcement	Mineral filler, 30% filler by weight		
Additive	Antistatic property		
Features	Antistatic property		
	Good UV resistance		
	Recyclable materials		
	Scratch resistance		
	Excellent appearance		
Uses	Handle		
	Car interior parts		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ISO 1133
Molding Shrinkage	0.70 - 1.1	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2050	MPa	ISO 527-2/2
Tensile Stress (Yield)	19.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	3.0	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
0°C	3.0	kJ/m ²	ISO 179/1eA

23°C	7.0	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	111	°C	ISO 75-2/B
1.8 MPa, not annealed	65.0	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	210 - 260	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			

Holding pressure: 50 to 70% of the injection pressure

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

