

PERLEX® R251

Polycarbonate
A. Schulman Europe

Message:

PERLEX® R251 is a Polycarbonate (PC) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary attribute of PERLEX® R251: Flame Rated.
Typical application of PERLEX® R251: Electrical/Electronic Applications

General Information			
UL YellowCard	E132739-222168		
Features	Medium Flow		
Uses	Electrical Parts		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	11	g/10 min	ISO 1133
Molding Shrinkage	0.50 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2350	MPa	ISO 527-2
Tensile Stress (Yield)	60.0	MPa	ISO 527-2
Tensile Strain (Break)	100	%	ISO 527-2
Flexural Modulus	2300	MPa	ISO 178
Flexural Stress	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	45.0	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	135	°C	ISO 75-2/B
1.8 MPa, Unannealed	125	°C	ISO 75-2/A
Vicat Softening Temperature	142	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-2		UL 94
Glow Wire Ignition Temperature			IEC 60695-2-13
1.00 mm	850	°C	
2.00 mm	850	°C	
3.00 mm	850	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

