

Michimid K4200GF13-02

Polyamide 66

API Polymers, Inc.

Message:

Michimid K4200GF13-02 is a Polyamide 66 (Nylon 66) product filled with 13% glass fiber. It is available in North America.

General Information			
Filler / Reinforcement	Glass Fiber,13% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	89.6	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus - Tangent	4690	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	243	°C	
1.8 MPa, Unannealed	238	°C	
Melting Temperature	265	°C	ASTM D789
Injection	Nominal Value	Unit	
Drying Temperature	93.3	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	293	°C	
Middle Temperature	288	°C	
Front Temperature	288	°C	
Nozzle Temperature	282	°C	
Processing (Melt) Temp	288	°C	
Mold Temperature	65.6	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT