

SCHULABLEND® (ABS/PA) M/MK K2004

Acrylonitrile Butadiene Styrene + Nylon

A. Schulman Europe

Message:

Easy flow high impact ABS/PA 6 blend; UV stabilised

General Information			
Additive	UV stabilizer		
Features	Impact resistance, high		
	Good liquidity		
Processing Method	Injection molding		
Part Marking Code (ISO 11469)	>ABS+PA		
Physical	Nominal Value	Unit	Test Method
Density	1.08	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (250°C/5.0 kg)	13.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1650	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	44.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	4.0	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	18	kJ/m ²	ISO 179/1eA
23°C	80	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		ISO 179/1eU
23°C	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	75.0	°C	ISO 75-2/Af
Vicat Softening Temperature	129	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flammability Classification (1.60 mm)	HB		IEC 60695-11-10, -20
Flammability		mm/min	FMVSS 302
Additional Information			

- 1.)
- Not for use in food contact applications2.)
- Not for use in medical or pharmaceutical applications

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT