

NuSil MED50-5338

Silicone Rubber, LSR

NuSil Technology

Message:

NuSil Technology's unrestricted materials may be considered for long-term implant applications (greater than 29 days). Liquid silicone rubbers, or LSRs, are elastomer systems reinforced with silica. They contain functional polymers of lower average molecular weight and viscosity when compared to high consistency rubbers (HCRs). They are typically supplied as two-component systems and formulated in a 1:1 mix ratio. Because their consistency is akin to petroleum jelly, they are often pumped with injection molding equipment to form molded components such as o-rings, gaskets, valves, seals, and other precision molded parts. LSRs are designed for liquid injection molding (LIM) processes which may utilize single or multi-cavity molds, or for overmolding processes. Originally designed for automated systems, they are developed with high volume applications in mind and benefit from their high strength.

Comments: FLUROSILICONE

General Information		
Filler / Reinforcement	Silica	
Features	Fast Cure	
	Good Colorability	
	High Strength	
Uses	Gaskets	
	Medical/Healthcare Applications	
	Overmolding	
	Seals	
	Valves/Valve Parts	
Agency Ratings	USP Class VI	
Forms	Liquid	
Processing Method	Liquid Injection Molding (LIM)	
Mechanical	Nominal Value	Unit
Tensile Strength (200% Strain)	1.59	MPa
Thermoset	Nominal Value	Unit
Thermoset Components		
Part A	Mix Ratio by Weight: 1.0	
Part B	Mix Ratio by Weight: 1.0	
Additional Information	Nominal Value	Unit
Cure System	Platinum	
Extrusion Rate	90.0	g/min
Uncured Properties	Nominal Value	Unit
Density	1.26	g/cm ³
Curing Time (150°C)	0.50	hr
Pot Life (25°C)	600	min
Cured Properties	Nominal Value	Unit

Shore Hardness (Shore A)	30	
Tensile Strength	4.48	MPa
Tensile Elongation at Break	350	%
Tear Strength	5.25	kN/m

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

