

TechnoPet GF 30 2 1

Polyethylene Terephthalate

TechnoCompound GmbH

Message:

TechnoPet: Attractive and cost effective

The TechnoPet compound line contains non-reinforced, glass fiber reinforced, impact strength modified as well as UV stabilized compounds for outdoor use.

TechnoPet compounds offer these properties:

- High stiffness
- High thermal stability >220°C
- Attractive surface
- High dimensional stability

For these reasons they represent an extremely cost effective solution compared with other technical compounds.

Typical Applications

Automotive industry: e.g. as a substitute for PA, engine covers...

Electrical engineering: e.g. lamp holders: glass fiber reinforced, flame retardant, high stiffness; multiple power sockets: modified impact strength, high dimensional accuracy...

Household appliances: e.g. steam irons: thermally stabilized PET compounds...

Packaging/logistics: e.g. logistic systems: modified impact strength, structural stability and strength...

Mechanical engineering: castors, bearings, gears, guide slide bearings...

General Information	
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight
Features	High Dimensional Stability
	Rigidity, high
	Insulation
	Thermal stability, good
	Good appearance
Uses	Packaging
	Gear
	Electrical/Electronic Applications
	Electrical appliances
	Application in Automobile Field
	Bearing

Physical	Nominal Value	Unit	Test Method
Density	1.61	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 2577
Transverse flow	1.1	%	ISO 2577
Flow	0.30	%	ISO 2577
Water Absorption			ISO 62
23°C, 24 hr	0.15	%	ISO 62
Saturated, 23°C	0.40	%	ISO 62
Viscosity Number (Reduced Viscosity)	60.0	ml/g	ISO 1628

Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness ²	240	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10200	MPa	ISO 527-2/1
Tensile Stress (Break)	150	MPa	ISO 527-2/5
Tensile Strain (Break)	2.1	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	8.0	kJ/m ²	ISO 179/1eA
23°C	8.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	29	kJ/m ²	ISO 179/1eU
23°C	30	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
1.8 MPa, not annealed	200	°C	ISO 75-2/A
8.0 MPa, not annealed	121	°C	ISO 75-2/C
Vicat Softening Temperature	230	°C	ISO 306/B50
Melting Temperature ³	240	°C	ISO 11357-3
CLTE - Flow (23 to 80°C)	2.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	IEC 60093
Volume Resistivity	> 1.0E+16	ohms·cm	IEC 60093
Dielectric Strength (1.00 mm)	31	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.30		IEC 60250
1 MHz	4.00		IEC 60250
Comparative Tracking Index (Solution A)	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.8 mm)	HB		UL 94
Glow Wire Flammability Index (2.0 mm)	750	°C	IEC 60695-2-12
NOTE			
1.	275°C / WZ 135 bzw. 100°C, 600 bar		
2.	358 N		
3.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

