

LNP™ THERMOCOMP™ LF006 compound

Polyetheretherketone

SABIC Innovative Plastics

Message:

LNP THERMOCOMP* LF006 is a compound based on Polyetheretherketone resin containing 30% Glass Fiber.

Also known as: LNP* THERMOCOMP* Compound LF-1006

Product reorder name: LF006

General Information			
UL YellowCard	E121562-101284444		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.54	g/cm ³	ASTM D792
--	1.53	g/cm ³	ISO 1183
Water Absorption			
24 hr, 50% RH	0.10	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.080	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	13200	MPa	ASTM D638
--	13100	MPa	ISO 527-2/1
Tensile Strength			
Break	176	MPa	ASTM D638
Break	175	MPa	ISO 527-2
Tensile Elongation			
Break	2.0	%	ASTM D638
Break	1.9	%	ISO 527-2
Flexural Modulus			
--	10800	MPa	ASTM D790
--	12700	MPa	ISO 178
Flexural Strength			
--	246	MPa	ASTM D790
--	264	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	120	J/m	ASTM D256
23°C ²	12	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	880	J/m	ASTM D4812

23°C ³	57	kJ/m ²	ISO 180/1U
Instrumented Dart Impact (23°C, Energy at Peak Load)	13.7	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	> 299	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	> 240	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	> 299	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	> 240	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	1.6E-5	cm/cm/°C	ASTM E831
Flow : -40 to 40°C	1.7E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	4.7E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	4.8E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value	Test Method	
Flame Rating (0.780 mm, Testing by SABIC)	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	150	°C	
Drying Time	4.0 to 6.0	hr	
Rear Temperature	370 to 380	°C	
Middle Temperature	380 to 400	°C	
Front Temperature	380 to 400	°C	
Mold Temperature	175 to 190	°C	
Back Pressure	0.300 to 0.700	MPa	
Screw Speed	60 to 100	rpm	
NOTE			
1.	5.0 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT