

EnCom POM 0614 TF

Acetal (POM) Homopolymer

EnCom, Inc.

Message:

PTFE Lubricated Homopolymer Acetal (POM)

General Information			
Filler / Reinforcement	Talc, 1.5% Filler by Weight		
Additive	PTFE Lubricant		
Features	Homopolymer		
	Lubricated		
Uses	Automotive Applications		
	Business Equipment		
	Sporting Goods		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/1.05 kg)	5.8	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow : 3.18 mm	1.7 to 2.0	%	
Across Flow : 3.18 mm	1.7 to 2.0	%	
Water Absorption			ASTM D570
24 hr	0.19	%	
Saturation, 23°C	0.86	%	
Equilibrium, 23°C, 50% RH	0.11	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3170	MPa	ASTM D638
Tensile Strength (Yield)	44.8	MPa	ASTM D638
Tensile Elongation (Break)	11	%	ASTM D638
Flexural Modulus	3120	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	69	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	164	°C	
1.8 MPa, Unannealed	98.3	°C	
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	185 to 199	°C	
Middle Temperature	185 to 199	°C	
Front Temperature	185 to 204	°C	
Nozzle Temperature	185 to 216	°C	
Processing (Melt) Temp	199 to 221	°C	
Mold Temperature	71.1 to 98.9	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

