

EcoLon® MRGF1878-BK1

Polyamide 6

Wellman Engineering Resins

Message:

EcoLon® MRGF1878-BK1 is a Polyamide 6 (Nylon 6) material filled with 30% glass\mineral. It is available in Asia Pacific, Europe, Latin America, or North America.

Typical application of EcoLon® MRGF1878-BK1: Automotive

General Information			
Filler / Reinforcement	Glass\Mineral,30% Filler by Weight		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Density	1.39	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.70 to 1.2	%	
Flow	0.30 to 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	108	MPa	ISO 527-2
Tensile Strain (Break)	2.8	%	ISO 527-2
Flexural Modulus	7250	MPa	ISO 178
Flexural Stress	214	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact Strength	5.6	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	188	°C	ISO 75-2/A
Melting Temperature	220	°C	ISO 3146

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT