

KumhoSunny PC/PBT HCB9330G

Polycarbonate + PBT

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

HCB9330G is a 30% glass fiber reforced PC/PBT alloy resin, offering high heat resistance, high mechanical strength and good chemical resistance. HCB9330G is recommended for automobile luggage carrier, household appliance, electrician products, etc.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Chemical Resistance		
	High Heat Resistance		
Uses	Automotive Applications		
	Electrical Parts		
	Electrical/Electronic Applications		
	Household Goods		
UL File Number	E254819		
	E65424		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.52	g/cm ³	ASTM D792
--	1.47	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			
250°C/5.0 kg	13	g/10 min	ASTM D1238
250°C/5.0 kg	15	g/10 min	ISO 1133
Molding Shrinkage			
Flow	0.30 to 0.50	%	ASTM D955
--	0.30 to 0.50	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
--	110	MPa	ASTM D638
--	115	MPa	ISO 527-2/5
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus			
--	6200	MPa	ASTM D790
-- ¹	8000	MPa	ISO 178

Flexural Strength			
--	155	MPa	ASTM D790
-- ²	170	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m ²	ISO 179
Notched Izod Impact			
3.20 mm	120	J/m	ASTM D256
23°C	11	kJ/m ²	ISO 180
Unnotched Izod Impact Strength (23°C)	60	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed	130	°C	ASTM D648
1.8 MPa, Unannealed ³	200	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	< 0.020	%	
Rear Temperature	230 to 260	°C	
Middle Temperature	240 to 275	°C	
Front Temperature	240 to 275	°C	
Nozzle Temperature	245 to 270	°C	
Processing (Melt) Temp	240 to 275	°C	
Mold Temperature	50.0 to 80.0	°C	
Back Pressure	0.300 to 1.00	MPa	
Screw Speed	30 to 70	rpm	
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		
3.	120°C/h		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT