

NILENE® P

Polypropylene Homopolymer

Taro Plast S.p.A.

Message:

Polypropylene homopolymer medium flow, flame rating UL94 HB.

General Information			
UL YellowCard	E143048-100035155		
Features	Homopolymer		
	Medium liquidity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Molding Shrinkage			Internal method
Vertical flow direction	1.4 - 1.8	%	Internal method
Flow direction	1.4 - 1.8	%	Internal method
Water Absorption (Saturation, 23°C)	0.030	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	25.0	MPa	ISO 527-2/50
Tensile Strain (Break)	30	%	ISO 527-2/50
Flexural Modulus ¹	1500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	40	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	125	°C	ISO 75-2/B
1.8 MPa, not annealed	60.0	°C	ISO 75-2/A
Vicat Softening Temperature	90.0	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	180 - 200	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			

Pre-heat Temperature: 70 to 90°CPre-heat Time: 1 hr

NOTE

1. 1.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

