

Veradel® 3300 PREM

Polyethersulfone
Solvay Specialty Polymers

Message:

Veradel® PESU was formerly marketed as Gafone™ PESU

Veradel® polyethersulfone (PESU) is transparent and offers high heat deflection temperatures, excellent toughness and dimensional stability, and resistance to steam, boiling water, and mineral acids. Other desirable properties include thermal stability, creep resistance, and inherent flame resistance. Veradel® 3200 is FDA compliant and therefore approved for direct food contact.

Veradel® 3200 is a low melt flow grade that can be processed by extrusion or injection molding. Veradel® 3300 is a medium melt flow grade suggested for general purpose injection molding. Veradel® 3400 is a high melt flow grade designed for easy molding of parts with thin walls or long flow lengths.

General Information			
UL YellowCard	E36098-100168882		
Features	Acid Resistant		
	Flame Retardant		
	General Purpose		
	Good Adhesion		
	Good Chemical Resistance		
	Good Creep Resistance		
	Good Dimensional Stability		
	Good Thermal Stability		
	Good Toughness		
	High Heat Resistance		
	High Tensile Strength		
	Hydrolysis Resistant		
	Medium Flow		
	Medium Molecular Weight		
	Medium Rigidity		
Uses	Food Service Applications		
	General Purpose		
RoHS Compliance	RoHS Compliant		
Appearance	Transparent - Slight Yellow		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (380°C/2.16 kg)	30	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.60	%	ASTM D955
Water Absorption (24 hr)	0.50	%	ASTM D570

Water Absorption - 30 days	1.9	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2690	MPa	ASTM D638
Tensile Strength	88.9	MPa	ASTM D638
Tensile Elongation (Yield)	6.5	%	ASTM D638
Flexural Modulus	2620	MPa	ASTM D790
Flexural Strength	125	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed)	200	°C	ASTM D648
CLTE - Flow	5.2E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.7E+15	ohms·cm	ASTM D257
Dielectric Strength	15	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	3.51		
1 kHz	3.50		
1 MHz	3.54		
Dissipation Factor			ASTM D150
60 Hz	1.7E-3		
1 kHz	2.2E-3		
1 MHz	5.6E-3		
Flammability	Nominal Value	Unit	Test Method
Flame Rating ¹ (1.50 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	177	°C	
Drying Time	2.5	hr	
Processing (Melt) Temp	343 to 385	°C	
Mold Temperature	149 to 163	°C	
Injection Rate	Fast		
Screw Compression Ratio	2.0:1.0		
NOTE			

1.

These flammability ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

