

# ALCOM® PC 740/4 UV WT1401-06LD

Polycarbonate  
ALBIS PLASTIC GmbH

Message:

ALCOM® PC 740/4 UV WT1401-06LD is a Polycarbonate (PC) product filled with filler. It is available in Asia Pacific, Europe, or North America. Applications of ALCOM® PC 740/4 UV WT1401-06LD include automotive and lighting applications.

Characteristics include:

- Flame Rated
- REACH Compliant
- RoHS Compliant
- UV Stabilized

| General Information                            |                         |                        |             |
|------------------------------------------------|-------------------------|------------------------|-------------|
| Filler / Reinforcement                         | Filler                  |                        |             |
| Additive                                       | UV Stabilizer           |                        |             |
| Uses                                           | Automotive Applications |                        |             |
|                                                | Lighting Applications   |                        |             |
| Agency Ratings                                 | EC 1907/2006 (REACH)    |                        |             |
| RoHS Compliance                                | RoHS Compliant          |                        |             |
| Appearance                                     | Translucent             |                        |             |
| Physical                                       | Nominal Value           | Unit                   | Test Method |
| Density                                        | 1.19                    | g/cm <sup>3</sup>      | ISO 1183    |
| Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)     | 17.0                    | cm <sup>3</sup> /10min | ISO 1133    |
| Mechanical                                     | Nominal Value           | Unit                   | Test Method |
| Tensile Modulus                                | 2400                    | MPa                    | ISO 527-2   |
| Tensile Stress                                 |                         |                        | ISO 527-2   |
| Yield                                          | 66.0                    | MPa                    |             |
| --                                             | 66.0                    | MPa                    |             |
| Tensile Strain                                 |                         |                        | ISO 527-2   |
| Yield                                          | 6.0                     | %                      |             |
| Break                                          | 70                      | %                      |             |
| Flexural Modulus                               | 2450                    | MPa                    | ISO 178     |
| Flexural Stress                                |                         |                        | ISO 178     |
| --                                             | 100                     | MPa                    |             |
| 3.5% Strain                                    | 76.0                    | MPa                    |             |
| Flexural Strain at Flexural Strength           | 7.0                     | %                      | ISO 178     |
| Fire Performance (1.00 mm)                     | passed                  |                        | FMVSS       |
| Half Power Angle - T(Y) <sup>1</sup> (1.00 mm) | 57.0                    | °                      |             |
| Impact                                         | Nominal Value           | Unit                   | Test Method |
| Charpy Notched Impact Strength                 |                         |                        | ISO 179/1eA |

| --                                                | 12            | kJ/m <sup>2</sup> |                |
|---------------------------------------------------|---------------|-------------------|----------------|
| -40°C                                             | 12            | kJ/m <sup>2</sup> |                |
| -20°C                                             | 12            | kJ/m <sup>2</sup> |                |
| Charpy Unnotched Impact Strength                  |               |                   | ISO 179/1eU    |
| --                                                | No Break      |                   |                |
| -40°C                                             | No Break      |                   |                |
| -20°C                                             | No Break      |                   |                |
| Thermal                                           | Nominal Value | Unit              | Test Method    |
| Heat Deflection Temperature (1.8 MPa, Unannealed) | 124           | °C                | ISO 75-2/A     |
| Vicat Softening Temperature                       | 142           | °C                | ISO 306/B50    |
| Flammability                                      | Nominal Value | Unit              | Test Method    |
| Flame Rating                                      |               |                   | UL 94          |
| 1.50 mm                                           | HB            |                   |                |
| 0.750 mm                                          | V-2           |                   |                |
| Glow Wire Flammability Index                      |               |                   | IEC 60695-2-12 |
| 1.00 mm                                           | 850           | °C                |                |
| 2.00 mm                                           | 850           | °C                |                |
|                                                   | 960           |                   |                |
|                                                   |               |                   |                |
|                                                   |               |                   |                |
| 3.00 mm                                           | 850           | °C                |                |
|                                                   | 960           |                   |                |
|                                                   |               |                   |                |
|                                                   |               |                   |                |
| 4.00 mm                                           | 850           | °C                |                |
| Optical                                           | Nominal Value | Unit              | Test Method    |
| Transmittance <sup>2</sup> (Total, 1000 μm)       | 55.0          | %                 | ISO 13468      |
| Haze <sup>3</sup> (1000 μm)                       | 95            | %                 | ISO 13468      |
| Injection                                         | Nominal Value | Unit              |                |
| Drying Temperature                                | 100 to 120    | °C                |                |
| Drying Time                                       | 2.0 to 3.0    | hr                |                |
| Suggested Max Moisture                            | 0.020         | %                 |                |
| Processing (Melt) Temp                            | 270 to 310    | °C                |                |
| Mold Temperature                                  | 80.0 to 110   | °C                |                |
| NOTE                                              |               |                   |                |
| 1.                                                | A, 2°         |                   |                |
| 2.                                                | A, 2°         |                   |                |
| 3.                                                | III. A, 2°    |                   |                |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT