

LNP™ THERMOTUF™ V1000UXC compound

Polyamide

SABIC Innovative Plastics

Message:

LNP THERMOTUF V1000UXC is a compound based on unfilled Super Tough Nylon resin. Added feature of this material is: UV Stabilized.

Also known as: LNP* THERMOTUF* Compound V-1000 UV HP

Product reorder name: V1000UXC

General Information			
Additive	UV Stabilizer		
Features	Good UV Resistance		
	Ultra High Toughness		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.07	g/cm ³	ASTM D792
--	1.08	g/cm ³	ISO 1183
Molding Shrinkage			
Flow : 24 hr	2.1 to 2.3	%	ASTM D955
Across Flow : 24 hr	2.5 to 2.7	%	ASTM D955
Across Flow : 24 hr	2.6	%	ISO 294-4
Flow : 24 hr	2.2	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.60	%	ASTM D570
Equilibrium, 23°C, 50% RH	1.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	1710	MPa	ASTM D638
--	1650	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	39.0	MPa	ASTM D638
Yield	41.0	MPa	ISO 527-2/5
Break ³	39.0	MPa	ASTM D638
Break	41.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	57	%	ASTM D638
Yield	150	%	ISO 527-2/5
Break ⁵	85	%	ASTM D638
Break	170	%	ISO 527-2/5
Flexural Modulus			

--	2070	MPa	ASTM D790
--	1700	MPa	ISO 178
Flexural Strength			
--	55.2	MPa	ASTM D790
--	53.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C)	No Break		ASTM D4812, ISO 180/1U
Instrumented Dart Impact			
23°C, Total Energy	49.8	J	ASTM D3763
--	49.4	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	192	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁶	150	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	193	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁷	147	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	1.4E-4	cm/cm/°C	ASTM E831
Flow : -40 to 40°C	1.3E-4	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	1.3E-4	cm/cm/°C	ASTM E831, ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	260 to 271	°C	
Middle Temperature	271 to 282	°C	
Front Temperature	288 to 299	°C	
Processing (Melt) Temp	271 to 293	°C	
Mold Temperature	48.9 to 93.3	°C	
Back Pressure	0.344 to 0.689	MPa	
Screw Speed	10 to 60	rpm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	Type I, 5.0 mm/min		
5.	Type I, 5.0 mm/min		
6.	80*10*4 mm		
7.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT