

Diakon® ST35G7

Polymethyl Methacrylate Acrylic

Lucite International Inc.

Message:

Diakon® ST35G7 is a Polymethyl Methacrylate Acrylic material. It is available in Europe.

Typical application of Diakon® ST35G7: Automotive

General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	2.9	g/10 min	ISO 1133
Water Absorption (Equilibrium, 23°C, 50% RH)	0.35	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	48		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	50.0	MPa	ISO 527-2
Tensile Strain (Yield)	25	%	ISO 527-2
Flexural Modulus	2100	MPa	ISO 178
Flexural Stress	67.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	64	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength	6.1	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	90.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	102	°C	ISO 306/A
--	91.0	°C	ISO 306/B
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ISO 489
Transmittance	90.0	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

