

NEXUS Reprocessed PC 15/10 RBK

Polycarbonate

Nexus Resin Group, LLC.

Message:

Wide spec, polycarbonate

Black Reprocessed Pellets

General Information			
Recycled Content	Yes		
Appearance	Black		
Forms	Pellets, Reprocessed		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10 to 20	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	58.6	MPa	ASTM D638
Flexural Modulus	2340	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	530	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	138	°C	
1.8 MPa, Unannealed	132	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT