

POCAN® KU 1-7625 901510

Polycarbonate + PBT

LANXESS Asia/Pacific

Message:

PBT+PC, 20 % glass fibers, injection molding, low tendency to warp, improved surface finish

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Good Surface Finish		
	Low Warpage		
Agency Ratings	EC 1907/2006 (REACH)		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.39	g/cm ³	ISO 1183
Apparent Density	0.70	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	30.0	cm ³ /10min	ISO 1133
Water Absorption			ISO 62
Saturation, 23°C	0.30	%	
Equilibrium, 23°C, 50% RH	0.10	%	
Viscosity Number (Reduced Viscosity)	62.0	ml/g	ISO 1628
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	5500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	85.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.4	%	ISO 527-2/5
Flexural Modulus ¹ (23°C)	5500	MPa	ISO 178/A
Flexural Stress ² (23°C)	140	MPa	ISO 178/A
Flexural Strain at Flexural Strength ³ (23°C)	3.5	%	ISO 178/A
ISO Shortname	PBT+PC, GHMR, 09-050, GF20		ISO 7792
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	40	kJ/m ²	
23°C	40	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-40°C	< 10	kJ/m ²	

-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	40	kJ/m ²	
23°C	35	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	150	°C	ISO 75-2/B
1.8 MPa, Unannealed	115	°C	ISO 75-2/A
Vicat Softening Temperature	145	°C	ISO 306/B120
Melting Temperature ⁴	225	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	4.0E-5	cm/cm/°C	
Transverse : 23 to 55°C	7.0E-5	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.60 mm	HB		
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		
3.	2 mm/min		
4.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT