

Yuyao PPO SE1GFN3-780

Polyphenylene Ether + PS
Yuyao Tenglong Plastics Co., Ltd.

Message:

Yuyao PPO SE1GFN3-780 is a Polyphenylene Ether + PS (PPE+PS) product filled with glass fiber. It can be processed by injection molding and is available in Asia Pacific. Applications of Yuyao PPO SE1GFN3-780 include electrical/electronic applications and engineering/industrial parts.

Characteristics include:

Flame Rated
Eco-Friendly/Green
Halogen Free
Heat Resistant

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Environmentally Sound		
	Good Electrical Properties		
	Good Strength		
	Halogen Free		
	High Heat Resistance		
Uses	Electrical Parts		
	Structural Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	100	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	6000	MPa	ASTM D790
Flexural Strength	150	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area)	9.00	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	130	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.3E+3	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		

3.20 mm	V-0	
Injection	Nominal Value	Unit
Drying Temperature	100 to 115	°C
Drying Time	4.0 to 5.0	hr
Processing (Melt) Temp	250 to 280	°C
Mold Temperature	60.0 to 80.0	°C
Injection Pressure	70.0 to 100	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

