

ADDINYL A2 E

Polyamide 66

ADDIPLAST

Message:

ADDINYL A2 E is a Polyamide 66 (Nylon 66) material. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America.

Important attributes of ADDINYL A2 E are:

- Flame Rated
- Flame Retardant
- Halogen Free

General Information				
Additive		Flame Retardant		
Features		Flame Retardant		
		Halogen Free		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183/A
Hardness	Dry	Conditioned	Unit	Test Method
Shore Hardness (Shore D)	85	78		ISO 868
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress (Yield)	85.0	60.0	MPa	ISO 527-2
Tensile Strain (Break)	30	50	%	ISO 527-2
Flexural Modulus	2900	1300	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	5.0	11	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	No Break	No Break		ISO 179/1eU
Notched Izod Impact Strength	6.0	12	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	85.0	--	°C	ISO 75-2/Af
Melting Temperature (DSC)	260	--	°C	ISO 3146
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+15	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+14	ohms·cm	IEC 60093
Electric Strength	28	--	kV/mm	IEC 60243-1
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method

Flame Rating (1.60 mm)	V-2	--		UL 94
Glow Wire Ignition Temperature	960	--	°C	IEC 60695-2-13
Oxygen Index	28	--	%	ISO 4589-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

