

Novodur® P2H-AT

Acrylonitrile Butadiene Styrene

Styrolution

Message:

Novodur P2H-AT is a general purpose injection molding grade providing high flow ability.

General Information	
UL YellowCard	E256400-520838
Features	General Purpose
	Good Stiffness
	High Flow
	High Gloss
Uses	Appliances
	General Purpose
	Sporting Goods
Forms	Pellets
Processing Method	Injection Molding
Multi-Point Data	Creep Modulus vs. Time (ISO 11403-1)
	Isochronous Stress vs. Strain (ISO 11403-1)
	Isothermal Stress vs. Strain (ISO 11403-1)
	Secant Modulus vs. Strain (ISO 11403-1)
	Shear Modulus vs. Temperature (ISO 11403-1)
	Specific Volume vs Temperature (ISO 11403-2)
	Viscosity vs. Shear Rate (ISO 11403-2)

Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	37.0	cm ³ /10min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	110	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	44.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield, 23°C	2.1	%	
Break, 23°C	> 15	%	

Flexural Modulus	2400	MPa	ISO 178
Flexural Stress	70.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	7.0	kJ/m ²	
23°C	16	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	80	kJ/m ²	
23°C	100	kJ/m ²	
Notched Izod Impact Strength			ISO 180/A
-30°C	7.0	kJ/m ²	
23°C	16	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Annealed	97.0	°C	ISO 75-2/B
1.8 MPa, Annealed	93.0	°C	ISO 75-2/A
Vicat Softening Temperature	98.0	°C	ISO 306/B50
CLTE - Flow	9.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength ¹ (1.50 mm)	34	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.00		
1 MHz	2.90		
Dissipation Factor			IEC 60250
100 Hz	5.5E-3		
1 MHz	6.0E-3		
Comparative Tracking Index	600	V	IEC 60112
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	220 to 260	°C	
Mold Temperature	70.0	°C	
Injection Velocity	240	mm/sec	
NOTE			
1.	Short Time		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

