

Grilon® TSS

Polyamide 66/6 Copolymer
EMS-GRIVORY

Message:

Grilon® TSS is a Polyamide 66/6 Copolymer (Nylon 66/6) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Grilon® TSS are:

Flame Rated

RoHS Compliant

Nucleated

Typical applications include:

Automotive

Electrical/Electronic Applications

Appliances

Consumer Goods

Engineering/Industrial Parts

General Information				
Additive	Nucleating Agent			
Features	Nucleated			
Uses	Appliance Components			
	Automotive Applications			
	Automotive Interior Parts			
	Connectors			
	Consumer Applications			
	Electrical/Electronic Applications			
	Engineering Parts			
	Industrial Applications			
	Power/Other Tools			
	Sporting Goods			
RoHS Compliance	RoHS Compliant			
Forms	Granules			
Processing Method	Injection Molding			
Multi-Point Data	Shear Modulus vs. Temperature (ISO 11403-1)			
	Specific Volume vs Temperature (ISO 11403-2)			
	Viscosity vs. Shear Rate (ISO 11403-2)			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.3	--	%	
Flow	1.1	--	%	
Water Absorption				ISO 62

Saturation, 23°C	9.0	--	%	
Equilibrium, 23°C, 50% RH	3.0	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	135	45.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2700	750	MPa	ISO 527-2
Tensile Stress				ISO 527-2
Yield	70.0	40.0	MPa	
Break	45.0	--	MPa	
Tensile Strain (Yield)	4.0	15	%	ISO 527-2
Nominal Tensile Strain at Break	25	> 50	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	6.0	7.0	kJ/m ²	
23°C	8.0	35	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	220	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	55.0	--	°C	ISO 75-2/A
Continuous Use Temperature				Internal Method
-- ¹	80.0 to 110	--	°C	
-- ²	180	--	°C	
Melting Temperature ³	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	8.0E-5	--	cm/cm/°C	
Transverse	1.2E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+13	1.0E+11	ohms·cm	IEC 60093
Electric Strength	26	25	kV/mm	IEC 60243-1
Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
Additional Information	Dry	Conditioned		Test Method

ISO Type	PA66+PA6, MHR, 14-030N	--	ISO 1874
NOTE			
1.	Long Term		
2.	Short Term		
3.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT