

LUVOCOM® 1301-9243

Polyphenylene Sulfide
LEHVOSS Group

Message:

LUVOCOM® 1301-9243 is a polyphenylene sulfide (PPS) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM®The main features of 1301-9243 are:

Conductivity
anti-warping
Good stiffness

Typical application areas include:
engineering/industrial accessories
Electrical/electronic applications
textile/fiber
Automotive Industry
business/office supplies

General Information			
Features	Heat conduction		
	Low warpage		
	Rigid, good		
	Good strength		
Uses	Plug		
	Textile applications		
	Engineering accessories		
	Switch		
	Application in Automobile Field		
	Business equipment		
	Medical/nursing supplies		
Appearance	Dark gray		
Physical	Nominal Value	Unit	Test Method
Density	1.99	g/cm ³	ISO 1183
Molding Shrinkage	0.40 - 0.80	%	DIN 16901
Water Absorption (23°C, 24 hr)	< 0.050	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	16000	MPa	ISO 527-2
Tensile Stress (Break)	58.0	MPa	ISO 527-2
Tensile Strain (Yield)	0.50	%	ISO 527-2
Flexural Modulus	14000	MPa	ISO 178
Flexural Stress	76.0	MPa	ISO 178
Flexural Strain at Flexural Strength	0.70	%	ISO 178

Maximum operating temperature-Short Term	240	°C	
Insulation Resistance		ohms	IEC 60167
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	6.0	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	220	°C	UL 746B
Thermal Conductivity ¹	14	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+4	ohms	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature			
Hot air dryer	100 - 140	°C	
Hot air dryer, B	50 - 90	°C	
Drying Time			
Hot air dryer	2.0 - 4.0	hr	
Hot air dryer, B	> 4.0	hr	
Rear Temperature	300 - 320	°C	
Middle Temperature	310 - 330	°C	
Front Temperature	320 - 340	°C	
Nozzle Temperature	320 - 340	°C	
Processing (Melt) Temp	330	°C	
Mold Temperature	150 - 180	°C	
Injection instructions			
<p>General</p> <p>In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines. Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.</p> <p>Lengthy dwell times for the melts in the cylinder should be avoided.</p> <p>Lower the temperatures during interruptions!</p> <p>Predrying (optional)</p> <p>It is advisable to predry the granulate with a suitable dryer immediately before processing.</p> <p>The granulate may absorb moisture from the air.</p> <p>Delivery Form & Storage</p> <p>Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.</p> <p>Preferably storage should be effected in dry and normally temperatured rooms</p> <p>Additional Information</p> <p>The material does not necessarily have to be predried; when originally sealed containers are used, this process may normally be omitted. Processing temperatures above 360°C may very rapidly cause thermal damage and should therefore be avoided.</p> <p>Post-crystallization may lead to warpage at elevated operating temperatures. This can be counteracted by suitable heat treatment.</p> <p>The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.</p> <p>High-temperature polymers place increased demands on the tool steels employed.</p> <p>Please contact us for further information.</p>			
NOTE			
1.	Hot-Disk, 60x60x3 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT