

KEP® 2380

Ethylene Propylene Diene Terpolymer

Kumho Polychem Co., Ltd.

Message:

Features:

Tailored molecular weight distribution grade, good processability, fast extrusion, fast vulcanization, quality consistency, productivity improvement, good processing, medium vulcanization speed

Applications:

60-70 shore a dense body sealings, radiator hose, molded goods, gaskets, sponge profile

General Information		
Features	Good Processability	
	Vulcanizable	
Uses	Automotive Applications	
	Gaskets	
	Hose	
	Seals	
	Weatherstripping	
	Windows & Doors	
Forms	Bale	
Processing Method	Extrusion	
	Injection Molding	
Physical	Nominal Value	Unit
Mooney Viscosity (ML 1+8, 125°C)	82	MU
Ethylene Content	56.0	wt%
Ethylidene Norbornene (ENB) Content	5.7	wt%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT