

TECHNYL® A 218 BLACK 21N

Polyamide 66
Solvay Engineering Plastics

Message:

TECHNYL® A 218 Black 21 N is an unreinforced polyamide 66, standard viscosity, heat stabilized for injection moulding. This grade offers all the primary properties of unreinforced polyamide 66. In addition, it has improved resistance to high temperature, and can be used for components which will withstand long-term temperature stresses.

General Information				
UL YellowCard		E44716-235568		
Additive		heat stabilizer		
Features		Heat Stabilized - Inorganic		
		Good demoulding performance		
Uses		Industrial application		
		General		
		Consumer goods application field		
Agency Ratings		EC 1907/2006 (REACH)		
		UL QMFZ2		
RoHS Compliance		RoHS compliance		
Appearance		Black		
		Natural color		
Forms		Particle		
Processing Method		Injection molding		
Multi-Point Data		Isothermal Stress vs. Strain (ISO 11403-1)		
Resin ID (ISO 1043)		PA66		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183/A
Water Absorption				ISO 62
23°C, 24 hr	1.3	--	%	ISO 62
Equilibrium, 23°C, 50% RH	2.9	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3300	1300	MPa	ISO 527-2/1A
Tensile Strength				
Yield, 23°C	85.0	--	MPa	ASTM D638
Yield, 23°C	90.0	60.0	MPa	ISO 527-2/1A
Fracture, 23°C	55.0	50.0	MPa	ISO 527-2/1A

Tensile Elongation				
Yield, 23°C	85	--	%	ASTM D638
Yield, 23°C	4.0	10	%	ISO 527-2
Fracture, 23°C	30	--	%	ASTM D638
Fracture, 23°C	> 20	> 300	%	ISO 527-2
Flexural Modulus				
23°C	3300	--	MPa	ASTM D790
23°C	3000	1300	MPa	ISO 178
Flexural Strength				
23°C	125	--	MPa	ASTM D790
23°C	120	70.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.5	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break	No Break		ISO 179/1eU
Notched Izod Impact				
23°C	80	--	J/m	ASTM D256
23°C	4.0	10	kJ/m ²	ISO 180
Unnotched Izod Impact Strength (23°C)	No Break	No Break		ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, not annealed	220	--	°C	ASTM D648
0.45 MPa, not annealed	200	--	°C	ISO 75-2/Bf
1.8 MPa, not annealed	82.0	--	°C	ISO 75-2/Af
Melting Temperature	263	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+15	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+16	ohms·cm	IEC 60093
Dielectric Strength (2.00 mm)	25	22	kV/mm	IEC 60243-1
Relative Permittivity	2.90	3.20		IEC 60250
Dissipation Factor	0.030	0.080		IEC 60250
Comparative Tracking Index				IEC 60112
Solution a	600	600	V	IEC 60112
Solution B	350	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.6 mm	V-2	--		UL 94
3.2 mm	V-2	--		UL 94

Glow Wire Flammability Index (1.6 mm)	650	--	°C	IEC 60695-2-12
Oxygen Index	26	--	%	ISO 4589-2
Injection	Dry	Unit		
Drying Temperature	80		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	265 - 275		°C	
Middle Temperature	270 - 280		°C	
Front Temperature	280 - 285		°C	
Mold Temperature	60 - 80		°C	
Injection instructions				

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

Injection Advice:
For unfilled polyamide, Solvay recommends the use of high alloy steel with a weak chromium content. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm). For Mould Temperature, in the case of parts where the surface roughness is required we can recommend a temperature of 90°C to 120°C with an optimum at 105°C.

The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT