

Pearlbond™ 101

Thermoplastic Polyurethane Elastomer (Polycaprolactone)

Lubrizol Advanced Materials, Inc.

Message:

Pearlbond® 101 is a linear, polycaprolactone-based polyurethane, supplied in form of small white granules, which combines a very high crystallization rate with a very high thermoplasticity level. It is used for Hot Melt adhesives.

Pearlbond® 101 is mainly used for making heat-sealable fabrics (thermobonding), obtained by coating processes such as scattering or dot-coating (powder or paste). In all cases, the product is previously ground into powder, by cryogenic grinding. The particle size of the powder will depend on the application technique to be used.

Pearlbond® 101 is used for textile coating for making shoe-stiffeners (toe puffs & counters), by extrusion or sintering process.

General Information			
Features	Crystalline		
	Good Adhesion		
	Heat Sealable		
Uses	Adhesives		
	Coating Applications		
	Fabrics		
	Footwear		
	Textile Applications		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	White		
Forms	Granules		
Processing Method	Coating		
	Extrusion		
	Scatter Coating		
	Sintering		
Physical	Nominal Value	Unit	Test Method
Density (20°C)	1.19	g/cm ³	ISO 2781
Melt Mass-Flow Rate (MFR) (170°C/2.16 kg)	30 to 60	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	51		ISO 868
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	63.0 to 67.0	°C	Internal Method
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity ¹ (160°C)	380	Pa · s	ISO 1133
Additional Information	Nominal Value	Unit	Test Method
Crystallization Rate	Very High		Internal Method

Softening Range	55 to 60	°C	Internal Method
Thermoplasticity	Very High		Internal Method
NOTE			
1.	2.16 Kg		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT