

Anjacom® 050/65S-UV

Polycarbonate + ABS
Almaak International GmbH

Message:

Anjacom® 050/65S-UV is a Polycarbonate + ABS (PC+ABS) material. It is available in Europe.
Important attributes of Anjacom® 050/65S-UV are:
Flame Rated
Good UV Resistance
UV Stabilized

General Information			
Additive	UV Stabilizer		
Features	Good UV Resistance		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.13	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	22.0	cm³/10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.50 to 0.70	%	
Flow	0.50 to 0.70	%	
Water Absorption			ISO 62
23°C, 24 hr	0.70	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2/1
Tensile Stress (Yield)	56.0	MPa	ISO 527-2/50
Tensile Strain (Break)	5.0	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	49	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	127	°C	ISO 75-2/B
1.8 MPa, Unannealed	105	°C	ISO 75-2/A
Vicat Softening Temperature	122	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Electric Strength	24	kV/mm	IEC 60243-1
Comparative Tracking Index	300	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	95.0	°C
Drying Time	2.0 to 5.0	hr
Suggested Max Moisture	0.020	%
Processing (Melt) Temp	250 to 280	°C
Mold Temperature	60.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT