# SIBUR Synthetic Rubber IR SKI-3 Group I

## Polyisoprene

**SIBUR** 

#### Message:

Cis-isoprene synthetic rubber with a minimum content of 1,4-bonds amounting to 96% is essentially a product of isoprene polymerization in solution in the presence of catalyst based on titanium compounds. It contains darkling antioxidant.

Product characteristics: Appearance - bale of gray color with shades of blue and brown color; weight of a bale -  $(30 \pm 1)$  kg; packing - a plastic container, a metal container; shelf life - two (2) year since the date of manufacture

General Information			
Additive	Oxidation resistance (1500 to 4000 ppm) 2		
Features	Antioxidation		
Appearance	Grey		
Forms	bag		
Physical	Nominal Value	Unit	Test Method
Mooney Viscosity (ML 1+4, 100°C)	76 - 85	MU	ASTM D1646
Stearic Acid	0.60 - 1.4	%	Internal method
Ash Content		%	ASTM D5667
Volatile Matter		%	ASTM D5668
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	> 7.00	МРа	ASTM D3403
Tensile Strength (Yield)	> 27.5	MPa	ASTM D3403
Tensile Elongation (Break)	> 500	%	ASTM D3403

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

