

MTEGRITY™ LDPE LD220AM

Low Density Polyethylene

M. Holland Company

Message:

Low Density Polyethylene
Good Toughness
Thermal Stabilizer
Blown Film
Containers and Bottles

General Information			
Additive	heat stabilizer		
Features	Low density		
	Thermal Stability		
	Good toughness		
Uses	Blown Film		
	Bottle		
	Container		
Forms	Particle		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.921	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
1% secant, MD	214	MPa	ASTM D882
1% secant, TD	255	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield	24.8	MPa	ASTM D882
TD: Yield	21.4	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	200	%	ASTM D882
TD: Fracture	550	%	ASTM D882
Dart Drop Impact	100	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD	350	g	ASTM D1922
TD	180	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	75		ASTM D2457

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

