

Xuchuan 1007N/B-5301

Thermoplastic Polyurethane Elastomer (Polyether)

Xuchuan Chemical (Suzhou) Co., Ltd

Message:

Xuchuan 1007N/B-5301 is a Thermoplastic Polyurethane Elastomer (Polyether) (TPU-Polyether) product. It is available in Asia Pacific. Typical application: Consumer Goods. Primary characteristic: good weather resistance.

General Information		
Features	Good Weather Resistance	
	Hydrolysis Resistant	
Uses	Footwear	
	Tires	
Physical	Nominal Value	Unit
Density	0.400 to 0.650	g/cm ³
Density		
A-1007N : 40°C	1.010 to 1.020	g/cm ³
B-5301 : 40°C	1.080 to 1.200	g/cm ³
Viscosity		
A-1007N : 40°C	400 to 800	mPa·s
B-5301 : 40°C	300 to 600	mPa·s
Akron Abrasion	0.0500 to 0.100	cm ³ /1.61 km
Cream Time	8.0 to 10.0	sec
End of Rise Time	1.0 to 1.2	min
Free Rise Foam Density	200 to 320	kg/m ³
Hydrolysis Strength Retention (70°C) ¹	> 90	%
Preheat Temperature		
Part A	50 to 60	°C
Part B	60 to 70	°C
Preheat Time		
Part A	2.0 to 4.0	hr
Part B	10.0 to 15.0	hr
Processing Temperature		
Part A	30 to 35	°C
Part B	35 to 40	°C
Resilience	30 to 40	%
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A)	50 to 80	
Elastomers	Nominal Value	Unit

Tensile Strength (Break)	3.00 to 5.00	MPa
Tensile Elongation (Break)	290 to 360	%
Tear Strength	10.0 to 20.0	kN/m
Thermoset	Nominal Value	Unit
Thermoset Components		
Part A	Mix Ratio by Weight: 100	
Part B	Mix Ratio by Weight: 91 to 93	
Demold Time	5.0 to 7.0	min
Injection	Nominal Value	Unit
Mold Temperature	35.0 to 45.0	°C
NOTE		
1.	168 hr, 95% RH	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT