

NOVADURAN® 5010GT15

Polybutylene Terephthalate

Mitsubishi Engineering-Plastics Corp

Message:

NOVADURAN® 5010GT15 is a Polybutylene Terephthalate (PBT) material filled with 15% glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding.

Important attributes of NOVADURAN® 5010GT15 are:

Flame Rated

Good Toughness

General Information			
UL YellowCard	E41179-100373391	E53664-243558	
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Features	Good Toughness		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm³	ISO 1183
Molding Shrinkage			
Across Flow : 2.00 mm	1.2	%	
Flow : 2.00 mm	0.60	%	
Water Absorption (Saturation, 23°C)	0.090	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5200	MPa	ISO 527-2
Tensile Stress (Break)	85.0	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	5000	MPa	ISO 178
Flexural Stress	135	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	40	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	212	°C	ISO 75-2/B
1.8 MPa, Unannealed	188	°C	ISO 75-2/A
Melting Temperature	224	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : -30 to 50°C	6.0E-5	cm/cm/°C	
Flow : -30 to 120°C	6.0E-5	cm/cm/°C	
Flow : 50 to 120°C	6.0E-5	cm/cm/°C	
Transverse : -30 to 50°C	8.0E-5	cm/cm/°C	

Transverse : -30 to 120°C	9.0E-5	cm/cm/°C	
Transverse : 50 to 120°C	1.0E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	3.0E+15	ohms	IEC 60093
Volume Resistivity	4.0E+15	ohms·cm	IEC 60093
Electric Strength			IEC 60243-1
1.00 mm	24	kV/mm	
2.00 mm	21	kV/mm	
Relative Permittivity (1 MHz)	3.20		IEC 60250
Dissipation Factor (1 MHz)	0.020		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	5.0 to 8.0	hr	
Rear Temperature	240	°C	
Middle Temperature	245	°C	
Front Temperature	255	°C	
Nozzle Temperature	255	°C	
Mold Temperature	80.0 to 100	°C	
Injection Pressure	20.0 to 150	MPa	
Screw Speed	80 to 120	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

