

Amilan® CM3501G50

Polyamide Copolymer

Toray Resin Company

Message:

Amilan® CM3501G50 is a Polyamide Copolymer (Nylon Copolymer) product filled with 50% glass fiber. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

Flame Rated

Copolymer

Good Aesthetics

General Information			
Filler / Reinforcement	Glass Fiber,50% Filler by Weight		
Features	Copolymer Pleasing Surface Appearance		
Part Marking Code	>PA-GF50<		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.59	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 3.00 mm ¹	0.50 to 0.70	%	
Flow : 3.00 mm ²	0.20 to 0.40	%	
Water Absorption (23°C, 24 hr)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (23°C)	205	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.2	%	ISO 527-2
Flexural Modulus (23°C)	14200	MPa	ISO 178
Flexural Stress (23°C)	315	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	23	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	223	°C	ISO 75-2/B
Melting Temperature	228	°C	DSC
CLTE - Flow	2.0E-5 to 3.0E-5	cm/cm/°C	ISO 11359-2
Specific Heat	1500	J/kg/°C	
Thermal Conductivity	0.40	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+12 to 1.0E+13	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
NOTE			

1.	80x80x3
2.	80x80x3mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

