

PENTAMID B GV30 H UV natural

Polyamide 6
PENTAC Polymer GmbH

Message:
Normal viscosity, heat and UV stabilised polyamide 6, 30% glass fiber reinforced

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Additive		heat stabilizer		
		UV stabilizer		
Features		Good UV resistance		
		Thermal Stability		
Agency Ratings		EC 1907/2006 (REACH)		
Appearance		Natural color		
Forms		Particle		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.36	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Transverse flow	0.70	--	%	ISO 294-4
Flow	0.50	--	%	ISO 294-4
Water Absorption				ISO 62
Saturated, 23°C	6.7	--	%	ISO 62
Equilibrium, 23°C, 50% RH	2.1	--	%	ISO 62
Viscosity Number	145	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	10000	5500	MPa	ISO 527-2/1
Tensile Stress (Break)	180	120	MPa	ISO 527-2/5
Tensile Strain (Break)	3.8	8.0	%	ISO 527-2/5
Flexural Modulus	8100	--	MPa	ISO 178
Flexural Stress	240	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	13	--	kJ/m ²	ISO 179/1eA
23°C	14	20	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU

-30°C	75	--	kJ/m ²	ISO 179/1eU
23°C	95	100	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	215	--	°C	ISO 75-2/B
1.8 MPa, not annealed	205	--	°C	ISO 75-2/A
Melting Temperature	222	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Dielectric Strength	32	--	kV/mm	IEC 60243-1
Dielectric Constant (1 MHz)	3.80	--		IEC 60250
Comparative Tracking Index	550	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.6 mm	HB	--		UL 94
3.2 mm	HB	--		UL 94
Additional Information	Dry	Conditioned		Test Method
ISO Shortname	PA6, MHRL, 14-100, GF30	--		ISO 1874
Injection	Dry	Unit		
Drying Temperature	80		°C	
Drying Time	3.0		hr	
Suggested Max Moisture	0.050 - 0.13		%	
Suggested Max Regrind	20		%	
Rear Temperature	265 - 285		°C	
Middle Temperature	270 - 295		°C	
Front Temperature	275 - 285		°C	
Processing (Melt) Temp	260 - 300		°C	
Mold Temperature	60 - 100		°C	
Injection Pressure	71.5		MPa	
Screw L/D Ratio	18.0:1.0 to 22.0:1.0			
Screw Compression Ratio	2.2:1.0 to 2.8:1.0			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT