

Lupoy® SC2202

Polycarbonate

LG Chem Ltd.

Message:

Description

Good Toughness, Good Impact, Chemical Resistance

Application

Moible Phone Housing

General Information			
UL YellowCard	E67171-100027246	E248280-100041002	
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Good Chemical Resistance		
	Good Toughness		
	High Impact Resistance		
Uses	Cell Phones		
	Electrical/Electronic Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.10 to 0.30	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	90.7	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	7.0	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	4510	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 3.20 mm)	147	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	210	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load ⁵ (0.45 MPa, Unannealed, 6.40 mm)	144	°C	ASTM D648
RTI Elec	80.0	°C	UL 746
RTI Imp	80.0	°C	UL 746
RTI Str	80.0	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94

0.750 mm	HB	
3.00 mm	HB	
Injection	Nominal Value	Unit
Drying Temperature	100 to 120	°C
Drying Time	3.0 to 5.0	hr
Suggested Max Moisture	< 0.020	%
Rear Temperature	280 to 295	°C
Middle Temperature	285 to 305	°C
Front Temperature	290 to 310	°C
Nozzle Temperature	290 to 305	°C
Processing (Melt) Temp	295 to 315	°C
Mold Temperature	100 to 140	°C
Back Pressure	0.981 to 3.92	MPa
Screw Speed	40 to 70	rpm
NOTE		
1.	5.0 mm/min	
2.	5.0 mm/min	
3.	1.3 mm/min	
4.	1.3 mm/min	
5.	18.6kg	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

