

RTP PP FR2 NAT

Polypropylene
RTP Company

Message:
Flame Retardant - Non-PBB/PBDE - UL94 - Value Product

General Information			
UL YellowCard	E84658-522956		
Features	Flame Retardant		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.930	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	1.5 to 2.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1030	MPa	ASTM D638
Tensile Strength	26.2	MPa	ASTM D638
Tensile Elongation (Yield)	> 10	%	ASTM D638
Flexural Modulus	1240	MPa	ASTM D790
Flexural Strength	37.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	37	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	1200	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	54.4	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength ¹ (in Oil)	20	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-2		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	191 to 232	°C	
Mold Temperature	32.2 to 65.6	°C	
Injection Pressure	68.9 to 103	MPa	
NOTE			
1.	Method A (Short-Time)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT