

LNP™ LUBRICOMP™ RVL29XXP compound

Polyamide 66

SABIC Innovative Plastics Europe

Message:

LNP VERTON RVL29XXP is a compound based on PA 66 resin, containing Long Glass Fiber, PTFE. Added features include; Internally Lubricated.

Also known as: LNP* LUBRICOMP* Compound RFL-8029

Product reorder name: RVL29XXP

General Information			
Filler / Reinforcement	Long Glass Fiber		
Additive	PTFE Lubricant		
Features	Lubricated		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.65	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 24 hr	0.48	%	
Flow : 24 hr	0.13	%	
Water Absorption			ISO 62
23°C, 24 hr	1.2	%	
Equilibrium, 23°C, 50% RH	0.46	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	231	MPa	ISO 527-2/5
Tensile Strain (Break)	2.3	%	ISO 527-2/5
Flexural Modulus ¹			ISO 178
--	13600	MPa	
60°C	11700	MPa	
100°C	10500	MPa	
150°C	9000	MPa	
200°C	8900	MPa	
Flexural Stress			ISO 178
--	361	MPa	
60°C	300	MPa	
100°C	256	MPa	
150°C	204	MPa	
200°C	162	MPa	
Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.39		
vs. Itself - Static	0.40		
Flexural Strain at Break ²			ISO 178

--	3.2	%	
60°C	3.6	%	
100°C	3.2	%	
150°C	3.5	%	
200°C	2.7	%	
Wear Factor - Washer	21.0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-40°C ³	28	kJ/m ²	
23°C ⁴	30	kJ/m ²	
Unnotched Izod Impact Strength ⁵			ISO 180/1U
-40°C	74	kJ/m ²	
23°C	82	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁶ (1.8 MPa, Unannealed, 64.0 mm Span)	258	°C	ISO 75-2/Af
CLTE			ISO 11359-2
Flow : 23 to 60°C	2.1E-5	cm/cm/°C	
Transverse : 23 to 60°C	4.9E-5	cm/cm/°C	
Specific Heat	1480	J/kg/°C	ASTM E1269
Thermal Conductivity	0.27	W/m/K	ASTM D5930
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm, Testing by SABIC)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	282 to 293	°C	
Middle Temperature	288 to 299	°C	
Front Temperature	288 to 299	°C	
Processing (Melt) Temp	288 to 304	°C	
Mold Temperature	93.3 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	2.0 mm/min		
2.	2 mm/min		
3.	80*10*3		
4.	80*10*4		
5.	80*10*4		
6.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

