

SUMIKASUPER® LCP E6807L

Liquid Crystal Polymer
Sumitomo Chemical Co., Ltd.

Message:

SUMIKASUPER LCP is a thermotropic liquid crystalline polyester, showing the highest heat resistance among engineering plastics.
SUMIKASUPER LCP E6807L is 35% reinforced with a combination of glass fiber and inorganic filler.

General Information			
UL YellowCard	E54705-100988632	E54705-100988633	E249884-100962035
	E249884-100962036		
Filler / Reinforcement	Glass fiber reinforced material, 35% filler by weight		
Features	Good dimensional stability		
	Low warpage		
	Low viscosity		
	High temperature strength		
	Weldable		
	Good formability		
	Good liquidity		
	Good heat aging resistance		
	Good adhesion		
Uses	Good chemical resistance		
	Heat resistance, high		
	Electrical/Electronic Applications		
	Electrical appliances		
	Engineering accessories		
	Application in Automobile Field		
Forms	Food container		
	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.67	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.11	%	ASTM D955
Transverse flow	0.63	%	ASTM D955
Water Absorption (Saturation)	0.020	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	101		ASTM D785
Mechanical	Nominal Value	Unit	Test Method

Tensile Strength	134	MPa	ASTM D638
Tensile Elongation (Break)	4.5	%	ASTM D638
Flexural Modulus (23°C)	12100	MPa	ASTM D790
Flexural Strength (23°C)	145	MPa	ASTM D790
Shear Strength	53.0	MPa	ASTM D732
Poisson's Ratio	0.41		ASTM E132
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (6.40 mm)	340	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	270	°C	ASTM D648
Linear thermal expansion coefficient			ASTM D696
Flow: 50 to 150°C	1.0E-5	cm/cm/°C	ASTM D696
Lateral: 50 to 150°C	6.3E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Constant			ASTM D150
1 kHz	4.30		ASTM D150
1 MHz	3.80		ASTM D150
Dissipation Factor			ASTM D150
1 kHz	0.020		ASTM D150
1 MHz	0.030		ASTM D150
Arc Resistance	180	sec	ASTM D495
Comparative Tracking Index (CTI)	150	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.280 mm)	V-0		UL 94
Oxygen Index	45	%	ASTM D2863
Additional Information			
Mold Shrinkage, Sumitomo Chemical Method, Machine Direction: 1.1 mils/inMold Shrinkage, Sumitomo Chemical Method, Transverse Direction: 6.3 mils/inFlexural Strength, ASTM D790, 392°F: 4206 psiFlexural Modulus, ASTM D790, 392°F: 652670 psi			
Injection	Nominal Value	Unit	
Drying Temperature	120 - 150	°C	
Drying Time	3.0	hr	
Suggested Max Regrind	30	%	
Rear Temperature	300 - 320	°C	
Middle Temperature	320 - 350	°C	
Front Temperature	340 - 370	°C	
Nozzle Temperature	340 - 370	°C	
Mold Temperature	70.0 - 160	°C	
Injection Pressure	78.0 - 157	MPa	
Injection Rate	Moderate-Fast		
Holding Pressure	20.0 - 39.0	MPa	
Back Pressure	0.980 - 4.90	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

